



AD Dispersions

Pigment Dispersions for Solvent-Based Applications

AD Dispersions are liquid pigment dispersion concentrates for tinting and masstone applications. AD Dispersions have exceptional compatibility in a wide range of solvent-based systems.

Vehicle: Modified Long Oil Alkyd

Solvent: Mineral Spirits



Code	Description	Color Index	Wt/Gal,Lbs	Specific Gravity	Pigment	% by Weight			% by Volume			VOC
						Vehicle Solids	Volatiles	Pigment	Vehicle Solids	Volatiles	Lbs/Gal	
AD 2106	RUTILE TiO ₂	WH6	14.95	1.79	63.45	22.32	14.23	28.64	41.54	29.82	2.13	255
EX 319	TONER FOR WHITE		7.95	0.95	3.00	69.10	27.90	2.00	63.60	34.40	3.06	367
AD 2335	TRANSPARENT YELLOW OXIDE	Y42	9.83	1.18	35.60	27.15	37.25	11.85	32.02	56.13	3.66	439
AD 2342	LIGHT LEMON YELLOW OXIDE	Y42	14.00	1.68	60.00	20.00	20.00	24.70	31.90	43.40	2.80	336
AD 23483	HANSA YELLOW (GS)	Y73	8.52	1.02	30.75	36.75	36.27	20.95	36.00	43.05	2.81	337
AD 23490	ORGANIC YELLOW MEDIUM	Y74/Y65	9.17	1.10	40.00	24.80	35.20	23.40	28.40	48.20	3.20	383
AD 2365	LEAD-FREE YELLOW	Y65	9.28	1.11	44.20	20.10	35.70	28.20	24.80	47.00	3.31	397
AD 2374	HANSA YELLOW	Y74	8.20	0.99	30.00	30.00	40.00	20.00	29.20	50.80	3.28	393
AD 2455	DNA ORANGE	O5	9.23	1.12	42.24	32.78	24.98	29.02	35.37	35.61	2.33	279
AD 2500	TRANSPARENT RED OXIDE	R101	10.03	1.20	32.46	28.30	39.24	10.20	34.40	55.40	3.68	441
AD 2503	TOLUIDINE RED	R3	8.55	1.03	35.00	30.00	35.00	25.00	30.00	45.00	2.99	359
AD 25101	RED OXIDE LIGHT	R101	15.50	1.86	60.00	25.00	15.00	21.70	42.30	36.00	2.33	279
AD 25102	RED OXIDE MEDIUM	R101	15.78	1.89	63.50	24.00	12.50	26.00	43.80	30.20	1.99	239
AD 25122	QUINACRIDONE MAGENTA	R122	7.67	0.92	22.00	21.80	56.20	14.10	19.80	66.10	4.31	517
AD 25175	DEEP ORGANIC RED	R170	8.30	1.00	30.00	37.00	33.00	22.00	35.50	42.50	2.74	329
AD 2519	QUINACRIDONE RED	PV19	8.03	0.96	17.68	46.90	35.40	11.60	43.90	44.50	2.84	340
AD 2636	PHTHALO GREEN (YS)*	GR36	8.78	1.05	24.00	38.50	37.50	10.70	4.50	84.80	3.29	395
AD 267	PHTHALO GREEN	GR7	8.51	1.02	27.60	31.20	41.30	14.80	31.20	54.00	3.51	421
AD 2700	RAW UMBER	BR7	11.41	1.37	47.90	26.20	26.00	20.00	37.30	42.70	2.96	355

Our data is based on laboratory tests which are believed to be accurate. However, all recommendations are made without warranty since the conditions of use are beyond the control of Eagle Specialty Products. We do not assume any liability of the product relative to performance or injury resulting from its use. Liability, if any, is limited to replacement product. Lightfastness results are a relative guide based on the pigments used and final results are also influenced by the vehicle systems and UV packages used.



AD Dispersions

Pigment Dispersions for Solvent-Based Applications

Code	Description	Color Index	Wt/Gal,Lbs	Specific Gravity	Pigment	% by Weight		% by Volume			Lbs/Gal	VOC G/L
						Vehicle Solids	Volatiles	Pigment	Vehicle Solids	Volatiles		
AD 2711	BURNT UMBER	BR7	12.03	1.44	52.60	24.60	22.90	23.20	34.70	42.10	2.75	330
AD 27504	RAW SIENNA	Y43	12.34	1.48	51.20	28.90	19.90	21.20	44.30	34.50	2.45	294
AD 27516S	VAN DYKE BROWN (SYN)	N/A	9.79	1.18	32.67	37.38	29.95	11.72	43.23	45.05	2.93	351
AD 277	BURNT SIENNA	BR7	13.00	1.56	50.00	33.00	17.00	21.70	44.00	34.30	2.20	265
AD 2800	PHTHALO BLUE NFNC	B15.2	8.24	0.99	21.64	39.75	38.61	13.90	38.07	48.74	3.18	381
AD 28152	PHTHALO BLUE (RS)	B15.2	8.30	1.00	21.00	35.00	44.00	13.20	30.00	56.80	3.65	438
AD 28154	PHTHALO BLUE (GS)	B15.4	8.40	1.01	29.50	34.60	35.80	21.90	32.70	45.40	2.98	358
AD 2819	QUINACRIDONE VIOLET	V19	8.07	0.97	22.00	39.71	38.29	14.29	38.25	47.46	3.09	370
AD 2823S	CARBAZOLE VIOLET	V23	7.87	0.94	18.05	31.84	50.11	11.34	32.25	56.41	3.94	472
AD 2900M	MASSTONE BLACK	BK7	8.30	1.00	22.00	36.00	42.00	12.50	33.50	54.00	3.49	418
AD 2907	TRANSPARENT BLACK OXIDE	BLEND	9.09	1.09	19.00	59.30	21.70	5.00	64.70	30.30	9.09	237
AD 297T	TINTING BLACK	BK7	8.60	1.03	28.00	33.00	39.00	16.50	31.50	52.00	6.19	743
AD EX 1969-2	CARBON BLACK	BK7	8.82	1.06	35.00	29.40	35.60	20.60	31.20	48.20	3.14	377

*** MADE TO ORDER**

Our data is based on laboratory tests which are believed to be accurate. However, all recommendations are made without warranty since the conditions of use are beyond the control of Eagle Specialty Products. We do not assume any liability of the product relative to performance or injury resulting from its use. Liability, if any, is limited to replacement product. Lightfastness results are a relative guide based on the pigments used and final results are also influenced by the vehicle systems and UV packages used.